

SBR RUBBER 60 DUROMETER

COMMERCIAL RECYCLED RUBBER

ISO/ASTM DESIGNATION = SBR



Physical Characteristics:

Tensile: 500 PSI
 Elongation: 300%
 Hardness: 60 SHORE "A" +/-5
 Temperature Range: -30°C to 77°C (-22°F to 170°F)

Parts No.	Gauge x Width	Length	Wt. Per SF lbs.	Colour	Finish
SBRI60-.063-36	1/16" X 36"	100FT	0.47	Black	Smooth
SBRI60-.063-48	1/16" X 48"	100FT	0.47	Black	Smooth
SBRI60-.094-48	3/32" X 48"	66FT	0.71	Black	Smooth
SBRI60-.125-36	1/8" X 36"	66FT	0.94	Black	Smooth
SBRI60-.125-48	1/8" X 48"	66FT	0.94	Black	Smooth
SBRI60-.188-36	3/16" X 36"	66FT	1.41	Black	Smooth
SBRI60-.188-48	3/16" X 48"	66FT	1.41	Black	Smooth
SBRI60-.25-36	1/4" X 36"	50FT	1.89	Black	Smooth
SBRI60-.25-48	1/4" X 48"	50FT	1.89	Black	Smooth
SBRI60-.375-36	3/8" X 36"	50FT	2.83	Black	Smooth
SBRI60-.375-48	3/8" X 48"	50FT	2.83	Black	Smooth
SBRI60-.5-36	1/2" X 36"	50FT	3.77	Black	Smooth
SBRI60-.5-48	1/2" X 48"	50FT	3.77	Black	Smooth
SBRI60-.625-48	5/8" X 48"	50FT	4.71	Black	Smooth
SBRI60-.75-48	3/4" X 48"	50FT	5.66	Black	Smooth
SBRI60-1-48	1" X 48"	50FT	7.54	Black	Smooth
SBRI60-1.25-48	1-1/4" X 48"	9FT	9.43	Black	Smooth
SBRI60-1.5-48	1-1/2" X 48"	9FT	11.32	Black	Smooth
SBRI60-2-48	2" X 48"	9FT	15.09	Black	Smooth

NOTE: An economical, general-purpose 60 Durometer rubber sheet. This rubber offers solid resistance to abrasion and impact. It is not recommended for applications where oil or gasoline is present. SBR rubber sheet has good vibration and sound insulating properties.