

## HYPALON RUBBER 60 DUROMETER

ISO/ASTM DESIGNATION = CSM



### Physical Characteristics:

Tensile: 1100 PSI

Elongation: 300%

Hardness: 60 SHORE "A" +/-5

Temperature Range: -30°C to 120°C (-22°F to 248°F)

Parts No.	Gauge x Width	Length	Wt. Per SF lbs.	Colour	Finish
HYPI-.125-48	1/8" X 48	50FT	0.92	Black	Smooth
HYPI-.25-48	1/4" X 48	50FT	1.84	Black	Smooth

**NOTE:** This synthetic rubber offers exceptionally good resistance to weather, ozone, sunlight and oxidation. Hypalon has excellent properties for alkalis and acids. This sheet is not recommended for aldehydes, aromatic or chlorinated solvents. Hypalon rubber sheet is recommended for extended outdoor applications.