

NEOPRENE RUBBER 60 DUROMETER

COMMERCIAL GRADE
ISO/ASTM DESIGNATION = CR



Physical Characteristics:

Tensile: 620 PSI
Elongation: 300%
Hardness: 60 SHORE "A" +/-5
Tear Strength: 100PLI
Temperature Range: -40°C to +77°C (-40°F to +170°F)

Parts No.	Gauge x Width	Length	Wt. Per SF lbs.	Colour	Finish
NEOI60-.031-36	1/32" X 36"	100FT	0.23	Black	Smooth
NEOI60-.031-48	1/32" X 48"	100FT	0.23	Black	Smooth
NEOI60-.063-36	1/16" X 36"	100FT	0.46	Black	Smooth
NEOI60-.063-48	1/16" X 48"	100FT	0.46	Black	Smooth
NEOI60-.094-48	3/32" X 48"	66FT	0.69	Black	Smooth
NEOI60-.125-36	1/8" X 36"	66FT	0.92	Black	Smooth
NEOI60-.125-48	1/8" X 48"	66FT	0.92	Black	Smooth
NEOI60-.188-36	3/16" X 36"	66FT	1.38	Black	Smooth
NEOI60-.188-48	3/16" X 48"	66FT	1.38	Black	Smooth
NEOI60-.25-36	1/4" X 36"	66FT	1.84	Black	Smooth
NEOI60-.25-48	1/4" X 48"	66FT	1.84	Black	Smooth
NEOI60-.375-36	3/8" X 36"	33FT	2.72	Black	Smooth
NEOI60-.375-48	3/8" X 48"	33FT	2.72	Black	Smooth
NEOI60-.5-36	1/2" X 36"	33FT	3.64	Black	Smooth
NEOI60-.5-48	1/2" X 48"	33FT	3.64	Black	Smooth
NEOI60-.625-48	5/8" X 48"	33FT	4.53	Black	Smooth
NEOI60-.75-48	3/4" X 48"	33FT	5.48	Black	Smooth
NEOI60-1-48	1" X 48"	33FT	7.28	Black	Smooth
NEOI60-1.25-48	1-1/4" X 48"	9FT	9.09	Black	Smooth
NEOI60-1.5-48	1-1/2" X 48"	9FT	10.92	Black	Smooth
NEOI60-2-48	2" X 48"	9FT	14.57	Black	Smooth

NOTE: An economical 60 Durometer black rubber sheet that has been specifically formulated to provide moderate oil and petroleum based solvent resistance. In addition, this sheet gives good weathering and ozone resistance for outdoor or unusual environmental conditions. This material is utilized in a broad range of industrial applications from gasket making to the chemical and transportation industries.

